



# Gerber LexEdge™ II 5-mil

DESCRIPTION.....	1
INTENDED APPLICATIONS .....	1
PERFORMANCE LIFE .....	1
PRINTING .....	1
CUTTING .....	2
SHELF LIFE AND STORAGE .....	2
MAINTENANCE .....	3
PHYSICAL PROPERTIES.....	3
CHEMICAL RESISTANCE (UNPRINTED) .....	3
RELATED LITERATURE.....	3
CONTACT INFORMATION .....	3

## DESCRIPTION

LexEdge II 5-mil is a custom-formulated, LEXAN® based polycarbonate (LEXAN 8A35) designed for use with the GERBER EDGE®, GERBER EDGE 2®, and GERBER EDGE FX™ thermal transfer printing systems, in conjunction with GerberColor™ Foils.

LexEdge II 5-mil is dimensionally stable and resists tearing, abrasion, and heat. It has NOT been tested for FAA flame-retardancy effectiveness.

## INTENDED APPLICATIONS

LexEdge II 5-mil is ideally suited for the production of dynamic sub-surface graphics including membrane switches, keyboard overlays, architectural signs, and exhibit/display work. It is an excellent material option for producing small decals with a low profile for thinner, smoother-to-the-touch label applications.

## PERFORMANCE LIFE

Continuous exposure to ultra-violet light may cause discoloration; therefore, LexEdge II 5-mil is not recommended for outdoor or backlit applications.

## PRINTING

LexEdge II 5-mil has a light tack, protective mask on the print side of the material, which must be removed before printing. Mask should remain on any unused portion of the roll until time of printing.

Fine particles may be attracted to the surface of this material. If this occurs, LexEdge II 5-mil can be cleaned with distilled water and a lint-free cloth. Allow the material to completely dry before printing. Do not use an alcohol or solvent based cleaner on this product as they will cause the surface to haze and become unprintable.

If your software material selection palette does not have LexEdge II 5-mil, visit the Support Section of the Gerber Technology website – [www.gspinc.com](http://www.gspinc.com) – to download the latest settings.

The velvet side of this material will generally be the viewing side. Since the polished print surface is the opposite side and LexEdge II 5-mil will most often be used in second-surface applications, reverse-print procedures will need to be followed. LexEdge II 5-mil is shipped with the polished print surface rolled out.

When printing on LexEdge II 5-mil, a specific color of foil (usually white) will be used as a solid backing color. This color will generally be assigned as an overprint. In order to ensure that this color covers the other printed graphics as completely as possible, it may be necessary to alter its print settings. (This will be especially needed when the backing foil will be printed on top of more than two other colors.)

The print settings for the backing foil can be changed in the QuickPlot screen. Go into the "Print Order" screen (F11) and select SETTINGS. Click on "DARK" in the overprint side only.

GerberColor Spot (GCS), GerberColor Process Pro™ CMYK (GCP), and GerberColor Transparent (GCT) Series Foils can be used to print onto LexEdge II 5-mil.

## CUTTING

LexEdge II 5-mil should be score cut on any 15-inch EDGE-compatible sprocketed plotter or on the Gerber ODYSSEY™ Plotter. A 45° SuperSharp blade is recommended. Plotters should be set at 50% speed.

The ideal cut will penetrate halfway through the material. To punch out your finished pieces, find a straight cutline and fold the material backwards. Pinch the cut line with your fingers and the material will break. Slowly remove the finished piece one edge at a time. The user should perform a test cut to determine tool force setting.

If using a plotter with a swivel blade, you will be able to cut simple shapes easily. When cutting complex shapes, however, your ability to maintain an accurate and consistent cut depth may be compromised.

Cutting weed borders on LexEdge II 5-mil is not recommended or necessary.

## SHELF LIFE AND STORAGE

Store LexEdge II 5-mil in the plastic bag provided in the original shipping box. Printed or unprinted LexEdge II 5-mil should not be stored on a roll that has less than a 3-inch inside diameter.

Use a paper interleaf between printed materials that are rolled or stacked. Do not store printed graphics face to face. LexEdge II 5-mil should be stored in a clean area free from excessive moisture and sunlight. An ambient temperature below 100° F (38°C) is recommended. Unprinted LexEdge II 5-mil can be stored for one year at 70°F (21°C) and 50% relative humidity.

**CAUTION:** Polycarbonate film is commonly used in conjunction with sensitive electronic devices either as a label, window or membrane switch overlay. These devices or components of the same are often packaged in anti-static materials to protect the electronics against damage caused by electrostatic discharge (ESD). One type of anti-static packaging material is commonly referred to as **Pink Poly**. It is a clear pink (hot pink) polyethylene that is available as a film for bags, bubble pack or foam. It is treated with an amine type compound that imparts the anti-static qualities. This compound works by blooming to the surface of the polyethylene and together with airborne moisture produces ions that increases the electrical conductivity at the surface of the polyethylene. **All amines are chemically aggressive to polycarbonate.** A polycarbonate part that comes in contact with amines will eventually degrade. The degradation shows up as a surface haze or clouding, stress cracking of formed parts, complete ink

delamination or -in the advanced stages- de-polymerization of the polycarbonate. ***Pink Poly should not be used in close proximity to any polycarbonate product including hard-coated polycarbonate film.*** Anti-static packaging materials that are safe to use are those that are made conductive by using a metallized coating or inert conductive filler.

## MAINTENANCE

To clean printed graphics, use a mild, non-abrasive soap with a soft cloth or sponge. Avoid using alcohol-based cleansers or soaps containing grit or abrasives.

## PHYSICAL PROPERTIES

Thickness	5 mils
Film Color	velvet/polished

## CHEMICAL RESISTANCE (UNPRINTED)

Chemical Agent	Result
Mild Acids	No effect
Alcohol	Hazing
Alkalis	No effect at low concentration and below 85°F (29°C). Higher concentrations and temperatures result in physical decomposition.
Aliphatic Hydrocarbons	No effect
Amines	Crystallization
Aromatic Hydrocarbons	Severe stress cracking
Detergents and sprays	Mild soap solutions have no effect. Strongly alkaline materials should be avoided.
Esters	Crystallization
Ketones	Crystallization/stress cracking
Silicone oils/greases	No effect up to 85°F (29°C)

## RELATED LITERATURE

Refer to Product Bulletins of relevant foils and materials for product-specific handling, production, and finishing information.

## CONTACT INFORMATION

For help with questions concerning Gerber products, please call your distributor or Gerber Customer Service at 1-800-222-7446 or (860) 644-1551. Visit us on the Internet at [www.gspinc.com](http://www.gspinc.com) to learn more about our many other foils, materials and equipment.

EDGE, GERBER EDGE, GERBER EDGE 2, Gerber Scientific Products, GerberCal, GerberGraphics, GRAPHIX ADVANTAGE, GSP, and Images on Vinyl are Registered Trademarks of Gerber Technology.

Abrasion Guard, ColorSet, EDGE Positive, EDGE READY, Gerber AutoMag, GERBER EDGE FX, Gerber FastFacts, Gerber Guard, Gerber HoloGraphix, Gerber ImageCal, Gerber ImageCast, Gerber InstaChange, Gerber OMEGA, Gerber PermaGrip, Gerber PlastiGraphix, Gerber QUANTUM, Gerber Stardust, Gerber StrikeGuard, Gerber Tone, Gerber UVGuard, GerberCal, GerberColor, GerberColor Spectratone, GerberGauge, GerberGlow, GerberMag, GerberMask, GerberVision, GS 15, GS15plus, GSP Plot, GSxplus, GSx, ImagePerfect, IMAGE READY, LexEdge, Matched Technology System, MTS, ODYSSEY, OMEGA, Process Pro, SpectraShade, and SpectraTint are Trademarks of Gerber Technology.

PANTONE, and other Pantone, Inc., trademarks are the property of Pantone, Inc.

LEXAN is a Registered Trademark of General Electric Company.

**©2015 Gerber Technology. All Right Reserved**

<b>Category:</b> EDGE READY™	<b>FastFact #:</b> 5593	<b>Supplied by:</b> Aftermarkets	<b>Last Modified:</b> 09/03/15
------------------------------	-------------------------	----------------------------------	--------------------------------